Synthesis and Properties of a Novel Highly Thermal Stable

N-propargyl Monomer Containing Benzoxazole Ring

Guang Yang¹, Chengbo Wang¹, Chao Liu¹, Zhiyong Yang^{1,2}, Xianghui Hou³ ¹School of Material Science and Engineering, Beihang University, Beijing100191, China

²Center of Structure Composite Materials, Aerospace Research Institute of Materials

& Processing Technology, Beijing100076, China

³Faculty of Engineering, University of Nottingham, Nottingham, NG7 2RD, UK

Corresponding author:

Guang Yang, Key Laboratory of Aerospace Advanced Materials and Performance (Beihang University), Ministry of Education, School of Materials Science and Engineering, Beihang University, Beijing, 100191, China.

E-mail: yangguang@buaa.edu.cn

Abstract:

A novel highly thermal stable propargyl functional compound containing benzoxazole ring, N, N, N', N'-tetra propargyl-5-amino-2-(p-aminophenyl) benzoxazole (TPAPB), was proposed and synthesized using phase-transfer catalytic method. The cure behavior of TPAPB was investigated by non-isothermal differential scanning calorimetry analysis (DSC). The solubility and rheological properties of TPAPB, as well as its broad temperature window from 130 °C to 200 °C with low viscosity, offered excellent processability for TPAPB to be used as a potential monomer of thermosetting polymer resin. It was found that the glass transition temperature (T_g) of cured TPAPB was 359 °C, and the temperature of 5% weight loss (T_{d5}) was 418 °C in argon with the char residue up to 70% at 700 °C. The polymerized resin exhibited high heat resistance and thermal stability, together with its processability, making it good candidate as highly heat-resistant polymer matrix for advanced composite applications.

Keywords

Propargyl, Benzoxazole, Thermal stability, Phase-transfer catalysis, Purification

Instruction

Resins terminated with acetylene^{1, 2} or phenylacetylene^{3, 4} have a long shelf life and their cured products have excellent solvent resistance and favorable combination of physical and mechanical properties at high temperature. However, the small processing window is a major concern on processability of acetylene-terminated resins and the high cure temperature makes phenylacetylene-terminated resins less processable.⁵ Moreover, the high material cost also restricts their applications.⁶ In contrast to terminal acetylene or phenylacetylene functional resins, propargyl derivatives are much attractive for their easiness of synthesis and polymerization.⁷ Furthermore, excellent thermal and mechanical properties facilitate the resins suitable for composites,⁸ adhesives⁹ and special coatings.¹⁰

Many aromatic heterocyclic moieties, such as pyridine,¹¹ benzothiazole,¹² benzoxazole¹³ and benzimidazole,¹⁴ can improve thermal and mechanical properties of resins. Significant efforts have been paid on introducing an aromatic benzoxazole¹⁵ or benzobisxazole¹⁶ unit into the main chain of the polymer to improve thermal stabilities. In addition, most of the studies have been devoted to synthesis and polymerization of a few propargyl ether systems.^{17, 18} Liu *et al.*¹⁹ introduced benzimidazole moieties into the backbone of polyimide and the co-PI fibers exhibit extremely high tensile strength and initial modulus along with good thermal properties. Wang *et al.*²⁰ synthesized

high-temperature multiple-shape memory poly(benzoxazole-co-imide)s with superior thermal stability. The polymer possessed high tensile strength and good elongation.

However, one of the critical drawbacks of benzoxazole is its poor solubility in organic solutions due to its stiff structure, which is detrimental to its processability.²¹ From our previous results, the introduction of propargyl would enhance the solubility of highly heat-resistant resins and reduce the melting point of the monomers,^{22, 23} which is beneficial to their processing.

To achieve highly thermal stability, the present work aims on the synthesis of a novel monomer with a broad processing window. A propargyl-functional compound containing benzoxazole ring, N, N, N', N'-tetra propargyl-5-amino-2-(p-aminophenyl) benzoxazole (TPAPB) has been synthesized by phase-transfer catalysis method. The investigation involved the synthesis and characterization of TPAPB as well as the optimization of the reaction conditions. The properties of TPAPB and its polymerized product were also studied.

Experimental

Materials

Dichloromethane (AR, Beijing chemical works China), propargyl bromide (CP, Yangcheng Longsheng fine chemical works China), tetrabutyl-ammonium bromide (AR, Tianjin fine chemicals institute China), 2,4-diamino-phenol hydrochloride (Beijing chemical regent company China, recrystallized before further use), p-aminobenzoic acid (AR, Beijing Yili fine chemicals Co. Ltd China), phosphoric acid (AR 85%, Beijing chemical regent company China), stannous chloride (AR, Shantou Xilong Chemical Works China).

Measurements

¹H NMR spectrum was recorded on a FX-90Q 300 (300 MHz) with CDCl₃ as solvent. FT-IR spectrum was obtained from a Nicolet NEXUS-470 FT-IR spectrometer. Thermal analysis was performed on Differential Scanning Calorimetry (DSC) and Thermal Gravimetric Analysis (TGA) was conducted with a NETZSCH STA449C DSC-TGA analyzer, at a heating rate of 20 °C/min under argon atmosphere. The rheological characteristics of TPAPB were carried out on an Advanced Rheometric Expansion System rheometer under nitrogen atmosphere at a heating rate of 5 °C/min in a frequency of 1 Hz. The melting point was measured by an X-5 microscopic melting point apparatus.

Synthesis of 5-amino-2-(p-aminophenyl) benzoxazole

The reaction scheme for the synthesis of 5-amino-2-(p-aminophenyl) benzoxazole by dehydration-condensation reaction²⁴ was shown in Scheme 1.



Scheme 1. Synthesis of 5-amino-2-(p-aminophenyl) benzoxazole

First, polyphosporic acid was prepared as follows. Phosphorus pentoxide (60 g, 0.42 mol) was added in a 250mL three-necked, round flask with a nitrogen gas inlet tube. Then 85% phosphoric acid was injected into the reaction flask within 0.5 h, the flask was shaken so that the phosphorus pentoxide could be completely dissolved in phosphoric acid. The reaction mixture was slowly heated to 140 °C, stirred continuously and kept at this temperature for 4h. When the mixture changed to transparent, polyphosporic acid was obtained and then cooled to 60 °C. 2, 4-diamino-phenol hydrochloride (9.85 g, 0.05 mol), p-amino-benzoic acid (7.54 g, 0.055 mol) and stannous chloride (0.3 g, 1.58 mmol) were added to the flask respectively. The reaction was processed by vacuum pumping intermittently to remove hydrogen chloride in the temperature range of 60-110 °C for 12 h, and the reaction mixture was slowly heated to 200 °C for 5 h. Then the reaction mixture was cooled to 100 °C and poured into the mixture of ice and water. The sediment product was washed, neutralized by 10% sodium carbonate solution, repeatedly washed, air pump filtered, and dried in vacuum. Finally, a kind of yellow solid powder was obtained. Yield: 9.4 g, 83.6%. m.p.:230 \sim 231 °C. Elemental analysis, measured value (calculated value), %: C 68.87 (69.31); H 4.92(4.92); N 18.44 (18.66). ¹H-NMR (DMSO₂-d6, 300MHz), δ: 7.284, 7.313 (m, 1H, Ar-H); 6.796 (m, 1H, Ar-H); 7.757, 7.786 (d, 2H, J = 6 Hz); 5.643, (s, 4H, NH₂ × 2). IR (KBr), v, cm⁻¹: 3394, 3323, 1610, 1579, 1498, 1268, 950.

Synthesis of N, N, N', N'-tetra propargyl-5-amino-2-(p-aminophenyl) benzoxazole (TPAPB)

TPAPB was synthesized from 5-amino-2-(p-aminophenyl) benzoxazole and propargyl bromide by phase-transfer catalysis. The reaction scheme for synthesizing TPAPB was shown in Scheme 2.



Scheme 2. Synthesis of TPAPB

5-amino-2-(p-aminophenyl) benzoxazole, NaOH, deionized water, solvent and phase transfer agent were poured into a 100 mL three-neck bottom flask with a nitrogen gas inlet tube. Then propargyl bromide was added dropwise at 30 °C within 1 h under intensive stirring. The reaction mixture was continuously stirred at 20-50 °C for several hours. In each experiment, of bromide, the amount propargyl 5-amino-2-(p-aminophenyl) benzoxazole, NaOH, deionized water and solvent was 8.33 g (0.07 mol), 2.25 g (0.01 mol), 1.6 g (0.04 mol), 5.74 g, and 5.74 g, respectively. The different reaction conditions for synthesis of TPAPB were shown in Table I. On the completion of the reaction, the solvent layer was separated from aqueous layer and washed with deionized water three times.

No.	Solvent	Temp. (°C)	Alkali liquor	Phase transfer agent	Amount of phase transfer agent ^b (%)	Time (h)	Yield (%)
1	dichloromethane	20	NaOH	TBAB ^a	4.9	16	0
2	dichloromethane	50	NaOH	TBAB	4.9	11	95.3
3	DMF	70	NaOH	_	_	11	62.7
4	dichloromethane	50	NaOH	TBAB	2.5	11	54.1
5	dichloroethane	70	K_2CO_3	TBAB	4.9	11	66.9
6	dichloroethane	70	NaOH	TBAB	4.9	11	82.1
7	dichloromethane	50	K_2CO_3	TBAB	4.9	11	49.5
8	dichloromethane	50	KOH	TBAB	4.9	11	72.3

Table I. Different reaction conditions for the synthesis of TPAPB

^a Tetrabutyl-ammonium bromide was short for TBAB.

^b The amount of phase transfer agent was accounted for the amount of 5-amino-2-(p-aminophenyl)benzoxazole(mole fraction)

After distillation, a solid product was obtained, which was subjected to further purification and separation to obtain pure compound. Finally, a yellow solid powder was obtained. FT-IR and ¹H-NMR spectra were employed to determine the structure of the product.

Curing of TPAPB

The curing was carried out by heating the monomer in air by the following gradually heating procedure: 180 °C/1 h, 200 °C/2 h, 230 °C/2 h and 250 °C/10 h. Thereafter, the resin was post cured at 300 °C for 1 h. A black polymerized product was obtained.

Results and discussion

Synthetic reaction conditions of TPAPB

From the principle of phase-transfer catalysis, synthesis of TPAPB is a nucleophilic substitution reaction and 5-amino-2-(p-aminophenyl) benzoxazole is the nucleophile. To establish the optimum reaction conditions according to the yield of product, different methods have been applied to synthesize TPAPB by changing reaction conditions.

There are many clear advantages of phase-transfer catalytic method compared with other organic synthesis methods. It can reduce reaction time and lower reaction temperature. Moreover, the degree of reactions can be significantly increased because the catalysis can assist reactants to contact mutually. The reaction conditions of experiment No.3 to No.6 were same except the solvent and phase transfer agent. Owing to phase transfer agent, the yield of experiment No.6 (82.1%) was much improved from that of No.3 (62.7%).

Inherent characteristic of phase transfer agent is one of decisive factors to improve reaction rate. Usually, quaternary ammonium salt containing 15-25 carbon atoms has good catalytic effect²⁵ and the amount of salt account for 1-5% of reactant (mole fraction). Tetrabutyl-ammonium bromide was chosen as the phase transfer agent in this investigation for its approximate symmetry molecular structure. From experiment No.2

and No.4, it can be seen that when the amount of tetrabutyl-ammonium bromide was 4.9%, the yield was higher under the same conditions.

Generally speaking, all solvents used in phase transfer catalytic reaction are nonpolar or little polar, such as benzene, toluene, THF, dichloromethane, and dichloroethane, etc. Dichloromethane is the most commonly used solvent. Comparing experiment No.2 and No.6, it is found that the yield was increased when dichloromethane was used.

In the synthesis of TPAPB, the alkali liquor was another critical factor affecting the yield. From Table I, the yield of experiment No.8 (72.3%) was higher than that of No.7 (49.5%), and the yield of experiment No.2 (95.3%) was higher than that of No.8 (72.3%), indicating that NaOH was an optimal alkali liquor.

Purification and characterization of TPAPB

Thin layer chromatography and column chromatography were used for the purification in this study. Ethyl acetate/dichloromethane blended solvent with the volume ratio of 1:8 was used as developing solvent. The yield of purified product was 60%. The melting point of TPAPB was 125 °C, determined by the X-5 microscopic melting point apparatus.

Purified TPAPB can be verified from the spectra analysis of FT-IR and ¹H-NMR results: ¹H-NMR: δ (ppm): 2.25 (s, 4H, \equiv CH), 4.12 (s, 8H, -CH₂-). FT-IR: (KBr, cm⁻¹)

 \equiv C-H: 3276, C \equiv C: 2109. The FT-IR and ¹H-NMR spectra were shown in Figure 1 and 2, respectively.



Figure 1. The FT-IR spectrum of TPAPB



Figure 2. The ¹H-NMR spectrum of TPAPB

Solubility of TPAPB

The solubility of TPAPB was shown in Table II. The compound can be dissolved in many common solvents, such as acetone, dichloromethane, and Dichloroethane, etc. The result indicated that the propargyl groups incorporated into 5-amino-2-(p-aminophenyl) benzoxazole can improve the solubility of the product. Therefore, it is suitable for solution prepreg preparation in composite fabrication.

Table II. Solubility of TPAPB

Solvent	Acetone	CH_2Cl_2	CHCl ₃	DMF	Toluene	Ether	Ethanol
Solubility	++	++	++	++	+	+	

++ easily soluble, +- slightly soluble , -- unsoluble.

Rheological behavior of TPAPB

The viscosity of the TPAPB was measured at temperatures ranging from melting point (125 °C) to 257 °C (heating rate =5 °C/min) by an Advanced Rheometric Expansion System rheometer. The rheological curvet was shown in Figure 3.



Figure 3. Viscosity and complex modulus curves of TPAPB

The new synthesized compound, TPAPB, melt at about 125 °C. The viscosity was steadily below 0.1 Pa \cdot s in the range of 130-200 °C, and the viscosity increased quickly with temperature over 200 °C. A broad temperature window from 130 °C to 200 °C with low viscosity was suitable for resin transfer molding (RTM) process and the fabrication of thermosetting composite materials.

Cure behavior analysis

The cure of TPAPB is thermally activated, and both the polymerization and post cure proceed with no generation of by-products. The reaction behavior of the curing process was systematically studied. The non-isothermal differential scanning calorimetry (DSC) test was used to study the curing mechanism. The phenomenological kinetics of cure can be generally described as Eq. (1):

$$\frac{d\alpha}{dt} = \mathbf{K}(T)f(\alpha) = A\exp(-E_a/RT)f(\alpha)$$
(1)

where K(T) is reaction rate constant dependent on temperature, $f(\alpha)$ is the function of conversion(α) determined by the cure mechanism, A and E_a represent pre-exponential factor and activation energy of the Arrhenius equation respectively, R is the universal gas constant (8.3145 J·mol⁻¹·K⁻¹), and T is absolute temperature.



Figure 4. DSC curves of monomer TPAPB at different scanning rates

The kinetic parameters, activation energy and pre-exponential factor, were evaluated by Kissinger, Ozawa methods.^{23, 26, 27} The order of reaction (n) was calculated by Kissinger equation and Crane equation.²⁸ The dynamic DSC curves for TPAPB in the range of 25-350 °C at the heating rates of 5, 10, 15, 20 °C/min were presented in Figure 4. The data obtained from the curves were used to calculate the kinetic parameters. The results indicated that for calculating the activation energy value, both Kissinger and Ozawa's methods gave fairly close results: 145.91 and 147.43 kJ·mol⁻¹, respectively. The kinetic parameters were summarized in Table III.

Table III. Kinetic parameters of the cure reaction

parameter	Ea ^a (kJ·mol ⁻¹)	A (min ⁻¹)	n
value	145.91	4.20×10 ¹³	0.94

^a Obtained by Kissinger method.

Substituting the kinetic parameters into Eq. (1), the mathematic model of curing processes of TPAPB was obtained, as described in Eq. (2).

$$\frac{d\alpha}{dt} = 4.20 \times 10^{13} \exp\left(-1.76 \times 10^4/T\right) \left(1-\alpha\right)^{0.94}$$
(2)

By integrating the above kinetic equation (Eq. (2)), the function of the three variables (α , t, T) was derived in Eq. (3). The conversion-time relationships of the TPAPB for isothermal curing at 25, 40, 150, 200 and 240 °C were plotted in Figure 5. The figure showed that the compound cured in a relatively short period of time upon 200 °C but it kept extremely low conversion rate within a fairly long time when the temperature was below 40 °C. Considerable conversion did not occur at 25 °C after one year. It can be speculated that the newly synthesized compound can be stably stored for an incredibly long period at room temperature.



Figure 5. Conversion rate versus time at different curing temperatures: 25 °C, 40 °C,

150 °C, 200 °C, and 240 °C

According to the conversion-time relationship of TPAPB in figure 5, the conversion approached 100% rapidly within 2h at 240 °C. So the curing process could be: 180 °C/1 h, 200 °C/2 h, 230 °C/2 h and 250 °C/4 h.

The curing behavior of TPAPB was studied by FT-IR and DSC. The DSC curve was shown in Figure 6. The curing was completed with the end of the curing exothermic effect. The FT-IR spectra were shown in Figure 7. The disappearance of \equiv C-H and C \equiv C stretching vibrations at 3276 and 2109 cm⁻¹ indicated that propargyl groups had been completely converted during the thermal curing process. Cross-linking reaction involving C \equiv C bond might have occurred to form a thermally stable structure. Further study will be needed to clarify the mechanism of the reaction and the resulting thermal stability. The thermal polymerization is believed to proceed through addition reactions between the acetylene groups to form a conjugated polyene, ²⁹ which then participated in more complex reactions to yield crosslinked structures. Other reactions are also possible such as polycyclotrimerization reaction.³⁰ The plausible mechanism of the polymerization of TPAPB was demonstrated in Scheme 3.



Figure 6. DSC trace of TPAPB and the polymerized product (Ar, heating rate

20 °C/min)







Scheme 3. Plausible mechanism of the polymerization of TPAPB

Thermal properties of cured TPAPB

Thermogravimetric analysis (TGA) and differential scanning calorimetry (DSC) under argon were used to study the thermal properties of TPAPB. The DSC curve and TGA curve were shown in Figure 8 and Figure 9, respectively.

The results showed that the glass transition temperature (T_g) of cured TPAPB was 359 °C and there was no exothermal peak in DSC curve, exhibiting good thermal stability.



Figure 8. DSC of the cured TPAPB (Ar, heating rate 20 °C/min)



Figure 9. TGA result of the cured TPAPB (Ar, heating rate 20 °C/min)

 T_{d5} (temperature of 5% weight loss, determined by the TGA trace, under argon) was 418 °C, and the residue (under argon) at 700 °C was 70%. These values were much higher than those of the bis-propargyl ether resins, e.g. Dipropargyl ether of bisphenol A (DPEBA), of which residue at 700 °C was 57%.³¹ From these results, it can be drawn

that the benzoxazole and propargyl structures can increase the heat resistance and thermal stability of the resin, mainly because they are rigid groups and thermally stable structure might be formed by cross-linking reaction involving $C \equiv C$ bond.

Conclusions

N, N, N', N'-tetra propargyl-5-amino- 2-(p-aminophenyl) benzoxazole (TPAPB), a novel propargyl-terminated compound, was proposed and synthesized using phase-transfer catalytic method.

TPAPB can be dissolved in many common solvents, such as acetone, ethyl acetate, and dichloromethane, etc. The solubility and rheological properties of TPAPB, as well as its broad temperature window from 130 °C to 200 °C with low viscosity, offered excellent processability for TPAPB to be used as a monomer of thermosetting polymer resin. The curing behavior of TPAPB evaluated by nonisothermal DSC method showed that the apparent activation energies of the cure reaction were 145.9 kJ·mol⁻¹ and 147.4 kJ·mol⁻¹ determined by Kissinger and Ozawa methods respectively and that the novel compound possessed extraordinarily long shelf life. T_g of TPAPB was 359 °C, T_{d5} (the temperature of 5% weight loss, under argon) was 418 °C and the residue at 700 °C under argon was 70%. The polymerized product showed good heat resistance and thermal stability indicating that the resin has good potential to be used as thermal resistant polymer matrix for advanced composite applications.

Acknowledgements

This work was funded by the Aerospace Innovation Foundation of China.

References

- Li Q, Zhou Y, Hang XD, et al. Synthesis and characterization of a novel arylacetylene oligomer containing POSS units in main chains. *Eur Polym J* 2008; 44: 2538-2544.
- Huang JX, Du W, Zhang J, et al. Study on the copolymers of silicon-containing arylacetylene resin and acetylene-functional benzoxazine. *Polym Bull* 2009; 62: 127-138.
- Kimura H, Ohtsuka K, Matsumoto A, et al. Synthesis and characterization of phenylethynylcarbonyl terminated novel thermosetting imide compound. *Express Polym Lett* 2013; 7: 161-171.
- Yang Y, Fan L, Qu XM, et al. Fluorinated phenylethynyl-terminated imide oligomers with reduced melt viscosity and enhanced melt stability. *Polymer* 2011; 52: 138-148.
- 5. Hergenrother PM. The use, design, synthesis, and properties of high performance/high temperature polymers. *High Perform Polym* 2002; **15**: 3-45.
- Agag T and Takeichi T. Novel benzoxazine monomers containing p-phenyl propargyl ether: polymerization of monomers and properties of polybenzoxazines. *Macromolecules* 2001; 34: 7257-7263.

- Agag T and Takeichi T. Preparation, characterization, and polymerization of maleimidobenzoxazine monomers as a novel class of thermosetting resins. *J Polym Sci, Part A: Polym Chem* 2006; 44: 1424-1435.
- Ding YZ, Hu C, Guo X, et al. Structure and Mechanical Properties of Novel Composites Based on Glycidyl Azide Polymer and Propargyl-Terminated Polybutadiene as Potential Binder of Solid Propellant. *J Appl Polym Sci* 2014; 131: 40007-40014.
- He XZ, Yang XM and Jabbari E. Combined Effect of Osteopontin and BMP-2 Derived Peptides Grafted to an Adhesive Hydrogel on Osteogenic and Vasculogenic Differentiation of Marrow Stromal Cells. *Langmuir* 2012; 28: 5387-5397.
- 10. Kawanami T, Kawakami I, Sakamoto H, et al. Super environment-friendly electrodeposition paint. *Prog Org Coat* 2000; **40**: 61-62.
- Mehdipour-Ataei S and Gharehkhani E. Preparation of novel pyridine-based poly (ether amide) s via three different routes and investigation of their properties. *High Perform Polym* 2013; 25: 778-789.
- 12. Hu XD, Jenkins SE, Min BG, et al. Rigid-rod polymers: Synthesis, processing, simulation, structure, and properties. *Macromol Mater Eng* 2003; **288**: 823-843.
- Yang P and Gu Y. Synthesis of a novel benzoxazine-containing benzoxazole structure and its high performance thermoset. J Appl Polym Sci 2012; 124: 2415-2422.

- 14. Li K, Luo LB, Huang JY, et al. Enhancing mechanical properties of aromatic polyamide fibers containing benzimidazole units via temporarily suppressing hydrogen bonding and crystallization. *J Appl Polym Sci* 2015; **132**: 42482-42491.
- 15. Wang Y, Yu JR, Zhu J, et al. Hyperbranched polybenzoxazoles incorporated polybenzoxazoles for high-performance and low-K materials. *J Polym Sci, Part A: Polym Chem* 2015; **54**: 1623-1632.
- Intemann JJ, Hellerich ES, Tlach BC, et al. Altering the Conjugation Pathway for Improved Performance of Benzobisoxazole-Based Polymer Guest Emitters in Polymer Light-Emitting Diodes. *Macromolecules* 2012; 45: 6888-6897.
- Yang G, Zhou CG and Li B. Novel propargylether-terminated monomers containing pyridine and phenyl pendent group: Synthesis, cure, and properties. *J Appl Polym Sci* 2014; 131: 40469-40476.
- 18. Dhanalakshmi JP, Alam S and Vijayakumar CT. High temperature matrix resins based on bispropargyl ethers-part 1 Effect of copper salts on the thermal polymerisation of bispropargylether of bisphenol-A and the thermal stability of these polymers. *High Perform Polym* 2013; 25: 416-426.
- Luo LB, Zheng YX, Huang JY, et al. High-performance copoly (benzimidazole-benzoxazole-imide) fibers: Fabrication, structure, and properties. J Appl Polym Sci 2015; 132: 42001-42009.

- 20. Yang ZH, Chen Y, Wang QH, et al. High performance multiple-shape memory behaviors of Poly (benzoxazole-co-imide) s. *Polymer* 2016; **88**: 19-28.
- Wu J, Wang Y, Yu JR, et al. Synthesis of hyperbranched polybenzoxazoles and their molecular composites with epoxy resins. *J Appl Polym Sci* 2015; 132: 41942-41950.
- 22. Yang G, Li B, Zhang MN, et al. High heat-resistant linear propargyl ether-terminated polymers containing Si-H group: Synthesis, characterization, and properties. *High Perform Polym* 2013; **26**: 290-297.
- 23. Yang G, Yuan ZH, Yang ZY, et al. Nonisothermal Curing Kinetics of a Novel Polymer Containing Phenylsilylene and Propargyl-Hexafluorobisphenol A Units. J Appl Polym Sci 2013; 127: 3178-3185.
- 24. Preston J, DeWinter WF, Fofferbert WL, et al. Heterocyclic intermediates for the preparation of thermally stable polymers. III. Unsymmetrical benzoxazole, benzothiazole and benzimidazole diamines. *J Heterocycl Chem* 1969; **6**: 119-121.
- 25. Hashimoto T and Maruoka K. Recent development and application of chiral phase-transfer catalysts. *Chem Rev* 2007; **107**: 5656-5682.
- 26. Kissinger HE. Reaction Kinetics in Differential Thermal Analysis. *Anal Chem* 1957;
 29: 1702-1706.
- 27. Ozawa T. Kinetic analysis of derivative curves in thermal analysis. *J Therm Anal* 1970; 2: 301-324.

- 28. Crane LW, Dynes PJ and Kaelble DH. Analysis of curing kinetics in polymer composites. *J Polym Sci Polym Lett Ed* 1973; **11**: 533-540.
- 29. Liu JZ, Lam JWY and Tang BZ. Acetylenic Polymers: Syntheses, Structures, and Functions. *Chem Rev* 2009; **109**: 5799-5867.
- Zheng RH, Haussler M, Dong HC, et al. Synthesis, structural characterization, and thermal and optical properties of hyperbranched poly(aminoarylene)s. *Macromolecules* 2006; **39**: 7973-7984.
- 31. Nair CPR, Bindu RL, Krishnan K, et al. Bis propargyl ether resins: synthesis and structure–thermal property correlations. *Eur Polym J* 1999; **35**: 235-246.