

Coordination Chemistry of 2,2'-Bipyridyl- and 2,2':6',2''-Terpyridyl-Substituted BEDT-TTFs: Formation of a Supramolecular Capsule Motif by the Iron(II) Tris Complex of 2,2'-Bipyridine-4-thiomethyl-BEDT-TTF.

Qiang Wang,^a Lee Martin,^a Alexander J. Blake,^b Peter Day,^c Hiroki Akutsu^d and John D. Wallis^{a*}

^aSchool of Science and Technology, Nottingham Trent University, Clifton Lane, Nottingham NG11 8NS, UK


^bSchool of Chemistry, The University of Nottingham, University Park, Nottingham NG7 2RD, UK

^cUniversity College London, Department of Chemistry, 20 Gordon Street, London WC1H 0AJ, UK

^dDepartment of Chemistry, Graduate School of Science, Osaka University, 1-1 Machikaneyama-cho, Toyonaka, Osaka 560-0043, Japan

Abstract: Molecules of *tris*(2,2'-bipyridine-4-thiomethyl-BEDT-TTF)iron(II) (BEDT-TTF = *bis*(ethylenedithio)tetrathiafulvalene) assemble in pairs to form a novel supramolecular capsular structure in the solid state. Three BEDT-TTF residues from one complex lie in the three grooves between coordinated bipyridines of the other complex, and *vice versa*, to form a capsule with three-fold rotational symmetry and an internal volume of *ca.* 160 Å³. Further aspects of the coordination chemistry of this ligand, its 6-substituted isomer and the 2,2':6'2''-terpyridyl-4'-thiomethyl-BEDT-TTF analogue are described.

Introduction.




Scheme 1: Molecular structures of BEDT-TTF **1** and TTF-, EDT-TTF and BEDT-TTF donors functionalized with metal binding groups **2-8**.

BEDT-TTF **1** (Scheme 1) is a well-known organosulfur donor from which many radical cation salts and charge transfer compounds have been prepared.¹ Its radical cation salts, prepared by electrocrystallisation or diffusion with an electron acceptor, exhibit a wide range of electrical properties including conductivity, semi-conductivity and the formation of low temperature superconductors such as (BEDT-TTF)₂[Cu(NCS)₂].² The salts have been intensively studied to gain a better understanding of their different

electrical properties and the mechanisms underlying changes in those properties on variation of temperature or pressure, as well as to explore properties such as ferroelectricity³ and thermopower.⁴ For any particular counterion there can exist different stoichiometries, polymorphs and solvates, with different electrical properties. For example, the 1:1 salt with triiodide has been exploited by combination with fullerene C₆₀ to give a new conducting material,⁵ while the β -2:1 salt has been incorporated in a pressure sensor⁶ and used for the production of superconducting nanoparticles.⁷ BEDT-TTF is a component of several types of hybrid material such as paramagnetic superconductors prepared with iron(III) or ruthenium(III) *tris*-oxalates,⁸ and a material with coexisting conducting and ferromagnetic behavior composed of layers of BEDT-TTF and mixed metal (Mn(II)/Cr(III)) honeycomb oxalate layers.⁹ BEDT-TTF has also formed salts with chiral anions, including induction of anion chirality through use of a chiral solvent.¹⁰

In the radical cation salts, the BEDT-TTF donors usually pack in layers, involving the formation of parallel stacks to give a two-dimensional conducting network *via* short S \cdots S contacts, with different classes formed by variation in the orientation of the donors in the stack and between stacks as studied in detail by Mori.¹¹ In contrast, layers composed of face-to-face pairs organized edge-to-face are observed in superconducting materials such as (BEDT-TTF)₂[Cu(NCS)₂] (Scheme 2).² Addition of large substituents to the BEDT-TTF moiety mitigate against such packings, leading to pairing of donors, but two or more small substituents, e.g. methyl or hydroxymethyl, are tolerated.¹² It is of note that while the oxidized BEDT-TTF derivatives usually have a


planar organosulfur system, the neutral donors show more flexibility about the S...S vectors across the dithiole rings.¹³



Scheme 2. Two examples of the donor packing arrangements within layers in the crystal structures of BEDT-TTF radical cation salts: (a) for $(\text{BEDT-TTF})_2\text{B}_5\text{O}_6(\text{OH})_4$, the β -type packing arrangement involves parallel stacks of tilted donors, (b) for $(\text{BEDT-TTF})_2\text{Cu}(\text{NCS})_2$ the κ -type packing involves perpendicular arrangements of pairs of face-to-face oriented donors.¹⁴

Although a wide range of functionalized BEDT-TTF derivatives, including chiral ones, has been reported in recent years¹⁵ there is only one molecule reported, **2**, which contains more than one BEDT-TTF moiety.¹⁶ Attachment of several BEDT-TTFs together has the potential to apply a constraint to the organization of the molecules in the solid state and lead to new crystal packing arrangements, and thus new physical properties, for their radical cation salts. One way of achieving this is to functionalize BEDT-TTF with a group capable of binding to a metal ion and then form *bis* or *tris* complexes around the metal, and finally oxidize such materials to their radical cation

salts. Herein we report the production of a completely novel capsular motif by the *tris* iron(II) complex of BEDT-TTF functionalized with a 2,2'-bipyridine-4-thiomethyl group, **L**², a ligand whose synthesis we have reported along with those of two other BEDT-TTFs: the 6-thiomethyl isomer **L**¹ and the 2,2':6'2''-terpyridyl derivative **L**³ (Scheme 3).¹⁷ Other aspects of the coordination chemistry of this family of ligands are also reported. Other groups have attached metal binding groups to organosulfur donor molecules: a number of examples have involved pyridines or, in just a few cases, a 2,2'-bipyridine or a 2,2':6',2''-terpyridine as in **3-5**,¹⁸ as well as phosphines¹⁹ and their combination with other metal binding groups as in **6**,²⁰ and the use of 2,2'-bipyridines as linkers between TTFs²¹ and between TTF and a verdazyl radical as in **7** and **8** (Scheme 2).²² Lorcy *et al.* have extensively reviewed these types of material and their coordination chemistries.²³



Scheme 3. Molecular structures of novel donors **L**¹, **L**² and **L**³.

Discussion.

Tris complexes of ligand **L**² with first row divalent transition metal cations (Mn, Fe, Co, Ni, Cu, Zn) were prepared as their PF₆ salts in 61-95% yields by refluxing a

dichloromethane solution of three equivalents of the ligand \mathbf{L}^2 with a methanolic solution of the metal acetate, and precipitating the product by addition of ammonium hexafluorophosphate. Compositions were supported by microanalyses and observations of $[\text{M-PF}_6]^+$ and/or $[\text{M-2PF}_6]^{2+}$ ions in the electrospray mass spectra. After many attempts with these materials, solvated crystals of the *tris* complex with iron(II), $[\text{Fe}(\mathbf{L}^2)_3](\text{PF}_6)_2$, were obtained by slow diffusion of methanol into a nitrobenzene solution, and their composition studied by single crystal X-ray diffraction. The crystal structure is quite remarkable; *fac*-complexes have crystallized together in pairs to form a capsule motif (Fig. 1). The unsubstituted “ends” of three electron-rich BEDT-TTF groups of one $[\text{Fe}(\mathbf{L}^2)_3]^{2+}$ complex lie in the three grooves between the bipyridine groups around the iron cation of the other $[\text{Fe}(\mathbf{L}^2)_3]^{2+}$ complex and *vice versa*. The resultant interlocking of BEDT-TTF units and *tris*(bipyridyl)Fe(II) groups produces a “molecular container” with internal volume of approximately 160 \AA^3 . This is a totally new packing behavior for the BEDT-TTF molecule.

Crystals of solvated $[\text{Fe}(\mathbf{L}^2)_3](\text{PF}_6)_2$ are rhombohedral, space group *R*-3, with three capsule cations comprising six metals and eighteen ligands per unit cell, with the cation exhibiting crystallographic three-fold rotational symmetry with the rotation axis passing through the two iron centers generating a 50:50 mixture of Λ and Δ forms related via a crystallographic inversion centre. Difference electron density maps indicate there is some electron density inside the capsule. However, there is also a very considerable amount of space between the capsules in the crystal structure, comprising *ca.* 40% of the

unit cell volume, which is occupied by counterions (up to four per capsule) and solvents in a disordered way, for which no convincing structural model could be established. The




Figure 1. View of the $[\text{Fe}(\text{L}^2)_3]^{2+}$ complex with the three BEDT-TTF moieties directed forward (above), and view of the capsule $([\text{Fe}(\text{L}^2)_3]_2)^{4+}$ down the three fold rotation axis, showing how the three BEDT-TTF groupings from one complex lie between the bipyridyl groups of the other.




Figure 2. Space-filling view of the capsule with one ligand of L^2 shown in ball-and-stick mode to give a view of the inside of the capsule and of how the ligand coordinates to one Fe(II) and then positions its BEDT-TTF fragment between two bipyridyl groups at the second Fe(II) center.

PLATON/SQUEEZE²⁴ procedure was thus applied to the diffraction data, to exclude the solvent and the anions from the model. The results suggest > 3000 electrons per unit cell in the inter-capsular space, and *ca.* 56 electrons inside the capsule. We thus propose that the capsules are probably occupied by solvent (methanol) or in some cases by a PF_6^- anion (69 electrons). However, the limitations of the structural model do not justify a more detailed discussion of the contents. Nevertheless, despite the significant solvent and anion disorder, the cation geometry is well-defined.

The internal dimensions of the cavity of the capsule are *ca.* 6 Å along the three-fold axis and *ca.* 7 Å in directions perpendicular to this, corresponding to a volume *ca.* 160

\AA^3 . The PF_6^- anion has a volume of *ca.* 105\AA^3 and could feasibly be enclosed in a fraction of the capsules. The walls of the cavity are formed by the organosulfur portions of the substituted 1,3-dithiolo-1,4-dithiin units of six BEDT-TTF groups, and the capsule is closed top and bottom by the undersides of two *tris*(bipyridyl)Fe(II) units and their $-\text{SCH}_2-$ linkages to the BEDT-TTF units (Fig. 2). The rest of the organosulfur residue of each BEDT-TTF wraps around the outside of the bipyridines. The structure accommodates both enantiomers of the racemic ligand \mathbf{L}^2 which contains a stereogenic centre at the point of attachment of the side chain to the BEDT-TTF moiety. For the two enantiomeric forms, the locations of the bipyridine and most of the BEDT-TTF group are coincident, which is achieved by modifying the conformation of the dithiin ring so that




Figure 3. View showing how the two enantiomers of \mathbf{L}^2 are modeled, with the different positions for just the substituted ethylene bridge, side chain methylene group and one sulfur atom. Hydrogen atoms and a pyridine ring are omitted for clarity.

the $-\text{CH}_2\text{S}-$ side chain can take a pseudo-equatorial orientation for one enantiomer and a pseudo-axial orientation for the other enantiomer and so maintain very similar relative orientations of the BEDT-TTF and bipyridine units (Fig. 3). For a centrosymmetrically related ligand (space group $R-3$), there will be an opposite assignment of chirality to the pseudo-equatorial and pseudo-axial conformations.

The BEDT-TTF groups forming the capsule walls are slightly curved, with the central $\text{S}_2\text{C}=\text{CS}_2$ fragment of the TTF ring very nearly planar but with flexings of 14.9° and 20.2° about the $\text{S}\cdots\text{S}$ vectors across the two dithiole rings, so that the dithiole sulfur atoms are displaced inwards from the central $\text{S}_2\text{C}=\text{CS}_2$ plane by $0.717\text{--}1.134$ Å. The capsule formation is stabilized by interactions between the electron-deficient pyridine rings and the electron-rich BEDT-TTF groups belonging to the opposite iron complex. The unsubstituted “half” of each organosulfur donor lies in the cleft between two bipyridine rings making contact with one bipyridine system “face to face”, and directing its edge to the face of the second bipyridine ring (Fig. 2). One dithiole S atom, S4, is central to both interactions (Fig. 4). For the face-to-face interaction, this dithiole S atom lies over the center of the substituted pyridine ring at a perpendicular separation of 3.537 Å from its best plane, with shortest $\text{C}\cdots\text{C}$ contacts between the dithiole and pyridine rings of 3.429 and 3.512 Å. The terminal dithiole S atom, S2, lies over the space between the 3-H and 3'-H atoms of the bipyridine system ($\text{S}\cdots\text{H}$ 3.48 and 3.55 Å). The other S atom in the dithiole ring, S3, makes a $\text{S}\cdots\text{S}$ contact of 3.780 Å with the side-chain S atom connected to the pyridine ring. The edge of the donor makes shorter contacts to the face of the second bipyridine ring. Thus, dithiole sulfur atom S4 lies over the unsubstituted

pyridine ring at 3.312 Å above the best plane through the ring, with two particularly short S⋯C contacts of 3.436 and 3.437 Å, respectively, to the 5- and 6-C atoms of that pyridine ring. The observation of shorter S⋯C contacts from the edge of the donor rather than from its face is in accord with the asymmetric shape of the bonded divalent sulfur atom.²⁵ The edge-to-face contact is completed by sulfur atoms from the next dithiole and dithiin rings, S6 and S8, which lie 3.441 and 3.327 Å, respectively, from the bipyrindine plane, but the former is oriented over the space between the two 3- and 3'-hydrogen atoms (S⋯H 3.66 and 3.70 Å) and the latter lies close to the bond from the pyridine ring to the side chain S atom (S⋯C 3.624, S⋯S 3.706 Å). The Fe—N distances of 1.955(3) and 1.971(3) Å are typical for a low spin Fe(II) *tris*(bipy) complex (1.96 ± 0.04 Å).²⁶




Figure 4. Disposition of one BEDT-TTF residue in the cleft between two bipyrindine rings in $[\text{Fe}(\text{L}^2)_3]_2^{4+}$. BEDT-TTF residues are omitted from the bipyrindines and *vice-versa* for clarity.


There are no particularly short S...S contacts between donor moieties within the capsule, the shortest being 3.706(3) Å between a dithiin S atom and the side chain S of another BEDT-TTF unit. The shortest inter-capsule S...S contacts involve dithiole S atoms, and the three shortest lie in the range 3.594–3.648 Å.

Cyclic voltammetry of this series of complexes shows very similar oxidation potentials to BEDT-TTF with first and second oxidations typically at 0.56 and 0.88 V relative to Ag/AgCl (Table S1). Room temperature magnetic moments were also recorded (Table S2), and are consistent with those of *tris*(2,2'-bipyridyl) complexes.²⁷ Fe *tris*-bipyridine and its derivatives are well known to adopt low spin ($S = 0$) configurations with the high spin configuration only accessible as a short-lived excited state identified by femtosecond spectroscopy.²⁶ Variable temperature magnetic studies on $[\text{Fe}(\text{L}^2)_3](\text{PF}_6)_2$ revealed a weak Curie tail corresponding to trace paramagnetic impurity (*ca.* 1.2% $S = 2$ high spin Fe^{II} or 0.8% $S = 5/2$ Fe^{III}) coupled with a component arising from temperature independent paramagnetism (TIP). The exact value of the TIP term is difficult to determine due to uncertainty in the diamagnetic correction (residual lattice solvent, gelatin capsule etc.) but is of the order of 10^{-3} emu·mol⁻¹.

Although there is an extensive literature on the formation of molecular capsules,²⁸ to our knowledge none have been reported where the walls are formed mainly by organosulfur donors. Nevertheless, TTF-related species have found application in the preparation of cavitands, carcerands and also as functionalities for calixarene based sensors²⁹ and supramolecular applications of TTF have been reviewed.³⁰

Further coordination chemistry of ligand L^2 .

Ligand L^2 shows further coordination chemistry, for example forming 1:1 complexes with $M(\text{hfac})_2$ ($M = \text{Mn}, \text{Co}, \text{Ni}, \text{Cu}, \text{Zn}$)³¹ to give six-coordinate $[(L^2)M(\text{hfac})_2]$ complexes in 70-80 % yield, and with $\text{Nd}(\text{hfac})_3$ to give the eight-coordinate 1:1 complex $[(L^2)\text{Nd}(\text{hfac})_3]$ in 80% yield. The formulations of the complexes are supported by chemical analyses, and their mass spectra typically show peaks at m/z : $[M - \text{hfac}]^+$. The $[(L^2)M(\text{hfac})_2]$ complexes showed very similar cyclic voltammetry data to BEDT-TTF (Table S1), suggesting that coordination is taking place only at the N atoms, and that the materials are simple octahedral complexes with one bipyridine and two hfac ligands (Scheme 4). The magnetic moment of the complex with Co(II) is consistent with the lower ligand field strength of a $[M(\text{bipy})(\text{hfac})_2]$ complex compared to that in the *tris*(L^2) complex (Table S2). Ligand L^2 also formed $(L^2)_2\text{MnCl}_2$, a 2:1 complex with MnCl_2 , which is assigned as the *cis* complex by analogy with similar cases,³² and also $L^2\text{CuCl}_2$, a 1:1 complex with CuCl_2 .



Scheme 4: $[(L^2)M(\text{hfac})_2]$ complexes with divalent transition metal ions and the $[(L^2)\text{Nd}(\text{hfac})_3]$ complex with Nd(III).

Chemistry and crystal structure of 6-substituted bipyridyl ligand L^1 .




Figure 5. The molecular and crystal structures of ligand L^1 showing the weak 1,5 N \cdots H interaction (left) and the segregation of BEDT-TTF and bipyridine units (right).


In contrast to L^2 , it was not possible to isolate any stable complexes containing ligand L^1 , in which the BEDT-TTF-CH₂-S- side chain is attached to the 6-position of the bipyridine, in conditions which were successful for ligand L^2 . 6-Substitution does not necessarily prevent a bipyridine from coordinating.³³ In the crystal structure of ligand L^1 (Fig. 5) the side chain lies in a pseudo-equatorial position from the dithiin ring which adopts an approximate boat type conformation. The -S-CH₂- group takes an extended conformation and links to the *trans*-bipyridine system so that the S-CH₂ bond lies roughly *syn* to the adjacent CN bond of the pyridine ring. This leads to a short (1,5) N \cdots H contact of 2.37 Å between the ring N atom and the side chain methylene group; this weak hydrogen bond will be enhanced by electron donation from the side chain sulfur atom to the ring nitrogen atom. The pyridine and organosulfur residues are more or less segregated in the crystal structure. The lack of stability of complexes of L^1 may be

due to a number of factors including the bulk of the BEDT-TTF group and the weak intramolecular interaction discussed above. Furthermore, there may be a kinetic factor, since these large organosulfur units may aggregate in solution and shield the pyridine nitrogen atom from potential coordination sites. Unusual and unexpected chemistry has been observed before with the BEDT-TTF system.^{17,34}

Coordination chemistry of terpyridyl ligand L^3 .

As a comparison to L^2 , the coordination chemistry of ligand L^3 , which carries a terpyridyl ligand, with first row transition metals has also been investigated. *Bis* complexes of ligand L^3 with M(II) (M = Mn, Fe, Co, Ni, Cu, Zn) were prepared in 57-82% yields by refluxing a dichloromethane solution of two equivalents of the ligand with a methanolic solution of the metal acetate, followed by precipitation of the product with ammonium hexafluorophosphate. Compositions were supported by microanalyses, but we were unable to grow suitable crystals for structural characterization, possibly due to the presence of two diastereomers. It would be expected that the two terpyridyl groups would be roughly perpendicular to each other (Scheme 5). The cyclic voltammetry of these complexes shows that first oxidation potentials are *ca.* 0.03 V higher and the second oxidation potentials are *ca.* 0.08 V lower than those for BEDT-TTF (Table S1). The room temperature magnetic moments of the complexes are consistent with the higher ligand field of *bis*(terpy) complexes (Table S2).³⁵ The magnetic measurement of the Fe(II) complex showed similar behavior to the *tris*- L^2 derivative, i.e comprising a small concentration of a paramagnetic defect (0.6% high spin Fe^{II}) and a temperature

independent paramagnetism term of a comparable magnitude to that observed for the *tris*(L^2)Fe(II) complex.



Scheme 5: *Bis*-complexes of ligand L^3 with divalent transition metal ions.

Conclusion.

We have demonstrated that ligand L^2 is capable of forming a molecular capsule with Fe(II) when the counterion is PF_6^- . Two *tris* complexes of formula $[Fe(L^2)_3]^{2+}$ combine together with the three electron-rich organosulfur donors of one complex lying in the electron deficient grooves between the bipyridine groups of the other to form the capsule, and *vice versa*. The encapsulated volume could accommodate a PF_6^- ion but this could not unambiguously be confirmed from the X-ray structure determination. The capsular framework structure can accommodate either enantiomer of ligand L^2 at each site, by adjusting the conformation of the substituted dithiine ring, so that the side chain lies either pseudo-equatorial or pseudo-axial. The corresponding complexes with first row divalent metal ions Mn(II) and Co(II)-Zn(II) were prepared and may also possess

analogous structures, but we were unable to obtain crystals suitable for measurement. The oxidation potentials of the ligand are not affected by formation of these structures. Ligand \mathbf{L}^2 behaves as a typical 4-substituted bipy ligand, forming complexes of type $[(\mathbf{L}^2)\text{M}(\text{hfac})_2]$ ($\text{M} = \text{Mn(II)}, \text{Co(II)-Zn(II)}$) and $[(\mathbf{L}^2)_2\text{MnCl}_2]$, while its 6-substituted isomer did not form any complexes at all with divalent first row transition metal ions. The corresponding 4'-substituted terpy ligand formed *bis* complexes of type $[(\mathbf{L}^3)_2\text{M}](\text{PF}_6)_2$ ($\text{M} = \text{Mn(II)-Zn(II)}$) in which the ligand had a slightly higher first oxidation potential than BEDT-TTF.

The novel capsular structure of the complex $[(\mathbf{L}^2)_3\text{Fe(II)}]_2^{4+}$ opens up the possibility of new applications of the structurally flexible BEDT-TTF unit. Extension of the chains linking the bipyridine ring and BEDT-TTF group, for example by including aromatic rings, offers the opportunity to encapsulate larger species e.g. fullerenes. *Tris*-(BEDT-TTF)-functionalization of a template which did not stabilize capsule formation could lead to a species capable of accepting large electron-deficient species. Furthermore, the opportunity to address the BEDT-TTF units electrochemically offers the chance to bind or release such species. The preparation of charge transfer salts of the complexes described herein is in progress.

Experimental.

General. NMR spectra were measured on a JEOL ECLIPSE 400 spectrometer at 400 MHz for ^1H and at 100 MHz for $^{13}\text{C}\{^1\text{H}\}$ using CDCl_3 as solvent and tetramethylsilane (TMS) as standard unless otherwise stated, and measured in p.p.m. downfield from TMS with coupling constants reported in Hz. IR spectra were recorded on a Perkin Elmer Spectrum 100 FT-IR Spectrometer as KBr disks and are reported in cm^{-1} . Mass spectra were recorded at the EPSRC Mass Spectrometry Centre at the University of Swansea. Chemical analysis data were obtained from Mr Stephen Boyer, London Metropolitan University. Flash chromatography was performed on 40-63 silica gel (Merck). Ligands L^1 - L^3 were prepared according to the procedures previously reported.¹⁷ Cyclic voltammetry measurements were made using an $\mu\text{Autolab}$ type II from Metrohm Autolab B.V. Magnetic susceptibility measurements were performed with a Quantum Design MPSM2 SQUID magnetometer using randomly oriented polycrystalline material encased in aluminium foil at 0.1 Tesla.

Preparation of $[\text{M}(\text{L}^2)_3](\text{PF}_6)_2$.

$[\text{Zn}(\text{L}^2)_3](\text{PF}_6)_2$. A solution of zinc acetate (0.010 g, 0.046 mmol) in MeOH (2 mL) was added to a solution of ligand L^2 (0.081 g, 0.14 mmol) in CH_2Cl_2 (7 mL) and the mixture refluxed for 2 h. After stirring at room temperature overnight, addition of NH_4PF_6 (0.031 g, 0.19 mmol) in MeOH (3 mL) gave instant formation of yellow precipitate which was stirred for a further 1 h. The yellow solid was collected by filtration, washed with MeOH and then CH_2Cl_2 and dried under vacuum. Yield 0.070 g (72%). Calc. for $\text{C}_{63}\text{H}_{48}\text{F}_{12}\text{N}_6\text{P}_2\text{S}_{27}\text{Zn}\cdot\text{H}_2\text{O}$, C 35.55, H 2.37, N 3.95%, found C 35.40, H 2.28, N 3.64%;

m/z (ES^+) 1965 $[M-PF_6]^+$, 910 $[M-2 PF_6]^{2+}$; ν_{max} (KBr): 1592, 1571, 1437, 1408, 1016, 842, 788, 558 cm^{-1} ; 1H NMR (DMSO- d_6): δ = 7.35-8.90 (br, m, 21H, Ar- H_{21}), 4.12 (br, 3H, SCHCH $_2$), 3.25-3.95 (m, 24H, 12 xCH $_2$); $^{31}P\{^1H\}$ NMR (DMSO- d_6): δ = -142.84 (septet, J_{F-P} = 711 Hz, PF_6^-). The product was insoluble in normal organic solvents except DMSO. The following complexes were prepared following the same general procedure:

$[Mn(L^2)_3](PF_6)_2$: yellow solid, yield 61%; Calc. for $C_{63}H_{48}F_{12}MnN_6P_2S_{27}$, C 36.04, H 2.30, N 4.00%, found C 35.79, H 2.27, N 3.77%; m/z (ES^+) 1955 $[M-PF_6]^+$, 904 $[M-2 PF_6]^{2+}$; ν_{max} (KBr): 1590, 1570, 1436, 1407, 843, 789, 558 cm^{-1} .

$[Fe(L^2)_3](PF_6)_2$: from iron(II) chloride, purple solid, yield 70%; Calc. for $C_{63}H_{48}F_{12}FeN_6P_2S_{27}$, C 36.02, H 2.30, N 4.00%, found C 35.69, H 2.33, N 3.68%; m/z (ES^+) 904.9 $[M-2 PF_6]^{2+}$; ν_{max} (KBr): 1597, 1466, 1437, 1407, 843, 784, 558 cm^{-1} .

$[Co(L^2)_3](PF_6)_2$: brown-yellow solid, yield 95%; Calc. for $C_{63}H_{48}CoF_{12}N_6P_2S_{27}$, C 35.97, H 2.30, N 3.99%, found C 36.37, H 2.23, N 3.89%; m/z (ES^+) 1959 $[M-PF_6]^+$, 907 $[M-2 PF_6]^{2+}$; ν_{max} (KBr): 1592, 1570, 1534, 1472, 1437, 1409, 842, 788, 773, 558 cm^{-1} .

$[Ni(L^2)_3](PF_6)_2$: brown-yellow solid, yield 76%; Calc. for $C_{63}H_{48}F_{12}N_6NiP_2S_{27} \cdot H_2O$, C 35.67, H 2.38, N 3.96%, found C 35.36, H 2.21, N 3.67%; m/z (ES^+) 1959 $[M-PF_6]^+$, 907 $[M-2 PF_6]^{2+}$; ν_{max} (KBr): 1593, 1570, 1438, 1406, 842, 788, 558 cm^{-1} .

$[Cu(L^2)_3](PF_6)_2$: light-brown solid, yield 79%; Calc. for $C_{63}H_{48}CuF_{12}N_6P_2S_{27}$, C 35.89, H 2.29, N 3.99%, found C 35.66, H 2.28, N 3.71%; m/z (ES^+) 1962 $[M-PF_6]^+$; ν_{max} (KBr): 1595, 1570, 1438, 1406, 843, 788, 558 cm^{-1} .

Synthesis of $[(L^2)M(hfac)_2]$ complexes.

$[(L^2)Zn(hfac)_2]$ A solution of L^2 (0.074 g, 0.13 mmol) in dry CH_2Cl_2 (10 mL) was added to a solution of $Zn(hfac)_2 \cdot 2H_2O$ (0.065g, 0.13 mmol) in dry acetone (3 mL) and the solution was heated to reflux for 1 h under nitrogen followed by stirring for 20 h. at RT. Removal of solvents gave an orange solid which was extracted with Et_2O . Removal of Et_2O from the filtrate afforded an orange solid which was recrystallized from CH_2Cl_2/n -hexane to give $[Zn(L^2)(hfac)_2]$ as an orange powder (yield 0.12 g, 85%). Calc. for $C_{31}H_{18}N_2O_4F_{12}S_9Zn$: C 34.98, H 1.70, N 2.63%; found C 35.21, H 1.78, N 2.43%; ν_{max} (KBr): 1648, 1607, 1594, 1554, 1528, 1499, 1474, 1257, 1202, 1145, 1093, 792, 666, 584, 527 cm^{-1} ; 1H NMR ($CDCl_3$): δ = 8.68 (1H, br d, 4.4 Hz, 6'''-H); 8.48 (1H, d, 5.7 Hz, 6''-H), 8.17 (1H, br d, J = 8.0 Hz, 3'''-H), 8.11 (1H, dt, J = 7.6, 1.6 Hz, 4'''-H), 8.00 (1H, d, J = 1.6 Hz, 3''-H), 7.66 (1H, br t, J = 6.2 Hz, 5'''-H), 7.42 (1H, dd, 5.6, 1.6 Hz, 5''-H), 5.98 (2H, s, *hfac*), 3.81-3.87 (1H, m, 5-H), 3.62 (1H, dd, J = 14.2, 5.8 Hz, 5 CH_α S), 3.53 (1H, dd, J = 14.2, 8.8 Hz, 5- CH_β S), 3.42 (1H, dd, J = 13.6, 2.8 Hz, 6- H_α), 3.35 (1H, dd, J = 13.6, 4.4 Hz, 6- H_β), 3.28 (4H, s, 5'-,6- H_2); $^{13}C\{^1H\}$ NMR ($CDCl_3$): δ = 178.7 (q, $J_{C,F}$ = 33 Hz, *hfac* 4 x C=O), 154.0 (2'-,2'''-C), 149.4 & 148.4 (6'-,6''-C), 148.2 (4'-C), 140.3 (4''-C), 126.9 (5''-C), 122.5 (3''-C), 121.1 (5'-C), 117.8 (3'-C), 117.4 (q, $J_{C,F}$ = 284 Hz, *hfac*, 4 x CF_3), 114.0, 113.7, 113.1, 112.5, 112.1 (6 x SCS), 89.0 (*hfac*, 2 x CH), 41.0 (5-C), 34.9 & 33.3 (5- CH_2 , 6-C) x SCH_2), 30.1 (5'-,6'-C); m/z (ES^+): 855, 857, 859 $[M-hfac]^+$.

A series of further complexes were prepared by the same method in 70-80% yield.

$[(L^2)Mn(hfac)_2]$

Calc. for $C_{31}H_{18}N_2O_4F_{12}S_9Mn$: C 35.33, H 1.72, N 2.66%; found C 35.62, H 1.67, N 2.49%; ν_{max} (KBr): 1647, 1591, 1528, 1498, 1474, 1256, 1203, 1146, 793, 664, 584 cm^{-1} ; m/z (ES^+): 846 $[M-hfac]^+$.

$[(L^2)Co(hfac)_2]$

Calc. for $C_{31}H_{18}N_2O_4F_{12}S_9Co$: C 35.19, H 1.71, N 2.65%; found C 35.56, H 1.71, N 2.45%; ν_{max} (KBr): 1641, 1594, 1528, 1474, 1257, 1203, 1146, 793, 668, 585 cm^{-1} ; m/z (ES^+): 850 $[M-hfac]^+$.

$[(L^2)Ni(hfac)_2]$

Calc. for $C_{31}H_{18}N_2O_4F_{12}S_9Ni$: C 35.20, H 1.72, N 2.65%; found C 35.40, H 1.69, N 2.39%; ν_{max} (KBr): 1645, 1595, 1524, 1500, 1498, 1474, 1257, 1203, 1147, 792, 671, 587 cm^{-1} ; m/z (ES^+): 849, 851 $[M-hfac]^+$.

$[(L^2)Cu(hfac)_2]$

Calc. for $C_{31}H_{18}N_2O_4F_{12}S_9Cu$: C 35.04, H 1.71, N 2.64%, found C 35.33, H 1.70, N 2.49%; ν_{max} (KBr): 1670, 1662, 1654, 1650, 1598, 1550, 1528, 1491, 1258, 1203, 1147, 793, 667, 586 cm^{-1} ; m/z (ES^+): 854, 856 $[M-hfac]^+$.

Preparation of $[(L^2)Nd(hfac)_3]$

A solution of L^2 (0.025g, 0.043 mmol) in dry CH_2Cl_2 (7 mL) was added to a solution of $Nd(hfac)_3 \cdot 2H_2O$ (0.034 g, 0.042 mmol) dissolved in dry acetone (1.5 mL). The orange solution was heated to reflux for 3 h under nitrogen followed by stirring for 16 h at RT. Removal of solvents gave an orange solid which was extracted into a small amount of

DCM, *n*-hexane was layered onto the DCM solution and stored overnight at 0°C. The orange precipitate was collected by filtration washed with *n*-hexane and dried. Yield 0.046 g, (80%). Calc. for C₃₆H₁₉F₁₈N₂NdO₆S₉: C 32.02, H 1.42, N 2.07%, found C 31.88, H 1.34, N 2.10%; ν_{\max} (KBr): 1720, 1696, 1650, 1592, 1572, 1534, 1475, 1437, 1257, 1204, 1147, 1013, 797, 720, 660, 585 cm⁻¹. The solid was insoluble in MeOH, Et₂O, CH₃CN, soluble in acetone (but slowly decomposes), and less soluble in DCM and CHCl₃.

Preparation of [M(L³)₂](PF₆)₂.

[Zn(L³)₂](PF₆)₂: A solution of Zn(OAc)₂ (0.013 g, 0.056 mmol) in MeOH (2 mL) was added to a solution of ligand L³ (0.075 g, 0.12 mmol) in CH₂Cl₂ (7 mL) and the solution was refluxed for 2 h. After stirring at room temperature overnight, a solution of NH₄PF₆ (0.037 g, 0.22 mmol) in MeOH (3 mL) gave instant formation of a yellow precipitate which was stirred for a further 1 h. The yellow solid was collected by filtration, washed with MeOH and then CH₂Cl₂ and dried under vacuum. Yield 0.070 g (75%). Calc. for C₅₂H₃₈F₁₂N₆P₂S₁₈Zn: C 37.19, H 2.28, N 5.00%, found C 37.18, H 2.12, N 4.75%; . *m/z* (ES⁺) 1534 [M–PF₆]⁺, 695 [M–2PF₆]²⁺; ν_{\max} (KBr): 1593, 1570, 1544, 1475, 1420, 1016, 841, 788, 558 cm⁻¹; ¹H NMR (CD₃CN): δ = 8.54 (s, 4H, 2 x 3',5'-H), 8.39 (d, 4H, *J* = 8.0 Hz, major) & 8.43 (d, 4H, *J* = 8.0 Hz, minor) (2 x 3-,3''-H), 8.08-8.13 (m, 4H, 2 x 4-,4''-H), 7.80 (d, 4H, *J* = 4.4 Hz, 2 x 6-,6''-H), 7.31-7.37 (m, 4H, 2 x 5-,5''-H), 4.31-4.38 (m), 4.20-4.28 (m), 3.62-3.73 (m), 3.48-3.52 (m), 3.12-3.31 (m) (SCH & 4 x SCH₂, major and minor diastereomers); ¹³C{¹H} NMR (CD₃CN): major diastereomer δ = 161.1, 149.4, 148.9, 148.2, 141.6, 128.5, 123.6, 120.3 (2 x Ar-C₈), 114.0, 113.6, 112.1, 110.6,

109.2, 109.1 (6 x sp^2C , BEDT-TTF), 44.4 (SCH), 35.4 (SCH₂), 33.9 (SCH₂), 30.6 (SCH₂CH₂S); minor diastereomer δ = 160.8, 149.4, 148.9, 148.2, 141.7, 128.5, 123.7, 120.4 (2 x Ar-C₈), 114.1, 113.8, 112.5, 111.6, 109.8, 109.6 (6 x sp^2C , BEDT-TTF), 44.1 (SCH), 35.7 (SCH₂), 34.1 (SCH₂), 30.7 (SCH₂CH₂S); ³¹P{¹H} NMR (CD₃CN): δ = -143.17 (septet, J_{F-P} = 707 Hz, PF₆⁻).

The following complexes were prepared following the same general procedure:

[Mn(L³)₂](PF₆)₂: yellow solid, yield 63%; Calc. for C₅₂H₃₈F₁₂MnN₆P₂S₁₈·2.5H₂O, C 36.44, H 2.53, N 4.90%, found C 36.21, H 2.26, N 4.73%. m/z (ES⁺) 691 [M-2PF₆]²⁺; ν_{max} (KBr) 1591, 1570, 1541, 1476, 1418, 1014, 840, 788, 558 cm⁻¹.

[Fe(L³)₂](PF₆)₂: from iron(II) chloride, purple solid, yield 82%; Calc. for C₅₂H₃₈F₁₂FeN₆P₂S₁₈: C 37.40, H 2.29, N 5.03%, found C 37.38, H 2.40, N 4.97%; m/z (ES⁺) 1525 [M-PF₆]⁺; ν_{max} (KBr): 1600, 1560, 1533, 1466, 1424, 1397, 1122, 1108, 840, 785, 558 cm⁻¹.

[Co(L³)₂](PF₆)₂: light brown solid, yield 73%; Calc. for C₅₂H₃₈CoF₁₂N₆P₂S₁₈·H₂O: C 36.94, H 2.38, N 4.97%, found C 36.76, H 2.19, N 4.83%; m/z (ES⁺) 1526 [M-PF₆]⁺, 690 [M-2PF₆]²⁺; ν_{max} (KBr): 1596, 1569, 1542, 1473, 1420, 1121, 1017, 841, 787, 558 cm⁻¹.

[Ni(L³)₂](PF₆)₂: orange-yellow solid, yield 57%; Calc. for C₅₂H₃₈F₁₂N₆NiP₂S₁₈·H₂O: C 36.94, H 2.38, N 4.97%, found C 36.86, H 2.20, N 4.73%; m/z (ES⁺) 1525 [M-PF₆]⁺, 690 [M-2PF₆]²⁺; ν_{max} (KBr): 1595, 1570, 1543, 1474, 1420, 1016, 842, 788, 558 cm⁻¹.

[Cu(L³)₂](PF₆)₂: light-brown solid, yield 63%; Calc. for C₅₂H₃₈CuF₁₂N₆P₂S₁₈·H₂O: C 36.83, H 2.38, N 4.96%, found C 36.63, H 2.24, N 4.71%; m/z (ES⁺) 1532 [M-PF₆]⁺, 693 [M-2PF₆]²⁺; ν_{max} (KBr): 1595, 1571, 1542, 1474, 1420, 1020, 841, 788, 558 cm⁻¹.

Preparation of complexes of ligands L^2 with $MnCl_2$ and $CuCl_2$.

$[(L^2)CuCl_2]$: A solution of $CuCl_2 \cdot 2H_2O$ (11 mg, 0.068 mmol) in dry MeOH (3 mL) was added to a solution of L^2 (40.0 mg, 0.068 mmol) in dry DCM (10 mL) to give slow formation of a brown precipitate. The mixture was stirred in the dark under a N_2 atmosphere for 20 h. The precipitate was collected by filtration, washed with MeOH and then DCM, and dried *under vacuo* to give the product as a brown powder, (0.03g, 61.4%). Calc. for $C_{21}H_{16}N_2S_9CuCl_2$: C 35.06, H 2.24, N 3.89%; found C 35.24, H 2.14, N 3.69%; m/z (ES^+): 684 $[M - Cl]^+$, 584 $[M - CuCl_2]^+$; ν_{max} (KBr): 2915, 1594, 1569, 1534, 1467, 1437, 1404, 1317, 1284, 1166, 1115, 1052, 1026, 1012, 886, 818, 788, 772, 718, 597 cm^{-1} . The solid was insoluble in common organic solvents but reasonably soluble in DMSO and DMF.

$[Mn(L^2)_2Cl_2]$: A solution of $MnCl_2 \cdot 4H_2O$ (24.0 mg, 0.12 mmol) in MeOH (2 mL) was added to a CH_2Cl_2 (15 mL) solution containing L^2 (0.15 g, 0.25 mmol) to give an immediate orange precipitate. The mixture was stirred at RT for 2 h and the solid collected by filtration followed by washing with MeOH and then CH_2Cl_2 and dried under vacuum to give $[(L^2)_2MnCl_2]$. Yield 0.13 g, (80%). Calc. for $C_{42}H_{32}Cl_2MnN_4S_{18}$: C 38.93, H 2.49, N 4.32%, found C 38.49, H 2.49, N 4.10%; m/z (ES^+) 585 $[L^2 + H]^+$; ν_{max} (KBr): 2916, 1590, 1571, 1534, 1473, 1405 (br), 1314, 1285, 1259, 1118, 1052, 1012, 818, 790, 771, 714, 601 cm^{-1} .

X-Ray Crystallography.

$[(L^2)_3Fe(II)]_2 \cdot 4PF_6 \cdot (C_6H_5NO_2)_x \cdot (CH_3OH)_y$: Diffraction-quality single crystals were obtained from nitrobenzene/methanol. The structure was solved using SHELXS97³⁶ and refined using SHELXL97.³⁶ The crystal contained large voids occupied by disordered solvent molecules (methanol and nitrobenzene) and PF_6^- anions which could not be resolved, so the structure of the cation was refined after application of the SQUEEZE²⁴ program to exclude anions and solvents from the model. Both enantiomers of ligand L^2 are included in the model, with identical positions for all atoms except those of the substituted ethylene bridge, the side chain methylene carbon and the dithiin sulfur nearest to the substitution position. The unsubstituted ethylene bridge is disordered between two conformations.

Crystal data: $C_{63}H_{48}N_6S_{27}Fe \cdot (PF_6)_2$, $M_r = 2100.48$, trigonal, $a = b = 23.8874(12)$, $c = 36.086(4)$ Å, $V = 17832(2)$ Å³, $Z = 6$, $R\bar{3}$, μ (Mo- $K\alpha$) = 0.68 mm⁻¹, $T = 120$ K, 6963 unique reflections, 3760 with $F_o > 4\sigma(F_o)$, final $R_1 = 0.054$; $wR_2 = 0.14$, crystals from nitrobenzene/methanol. Illustrations were prepared using Mercury,³⁷ ORTEP-3 for Windows³⁸ and POV-RAY.³⁹

Crystal data for L^1 : $C_{21}H_{16}N_2S_9$, $M_r = 584.9$, monoclinic, $a = 17.2349(4)$, $b = 17.2808(4)$, $c = 7.9477(1)$ Å, $\beta = 92.095(15)^\circ$, $V = 2365.50(8)$ Å³, $Z = 4$, space group $P2_1/c$, $D_c = 1.64$ g cm⁻³, μ (Mo- $K\alpha$) = 0.86 mm⁻¹, $T = 120$ K, 5429 unique reflections, 4408 with $F_o > 4\sigma(F_o)$, final $R_1 = 0.044$, $wR_2 = 0.099$, crystals from DCM/hexane. Crystal data have been deposited at the Cambridge Crystallographic Data Centre with deposition numbers 968626-968627.

“Supporting Information Available: Listings of NMR and IR spectra for zinc complexes $[(L^2)_3Zn](PF_6)_2$, $L^2Zn(hfac)_2$ and $[(L^3)_2Zn](PF_6)_2$, tables of cyclic voltammetry data for ligands and complexes and room temperature magnetic moments for complexes, and u.v.-visible spectra for $[(L^2)_3Fe](PF_6)_2$, and $[(L^3)_2Fe](PF_6)_2$ This material is available free of charge via the Internet at <http://pubs.acs.org>.”

References and Acknowledgements.

We thank the Leverhulme Trust for a grant F/01374/B (JW). We thank the EPSRC National Crystallography Service (University of Southampton) and the EPSRC Mass Spectrometry Service (University of Swansea) for measurements. We thank Prof. J. M. Rawson for helpful discussions. We acknowledge the EPSRC Chemical Database Service at Daresbury⁴⁰ for access to the Cambridge Structural Database.^{14a} The work has benefited from support from ESF COST action D35.

References

1. (a) Singleton, J.; Mielke, C. *Cont. Phys.* **2002**, *43*, 63-96, & *Physics World*, **2002**, *15*, 35-39. (b) Day, P. *Comp. Rend. Chem.* **2003**, *6*, 301-308.
2. (a) Williams, J. M.; Schultz, A. J.; Geiser, U.; Carlson, K. D.; Kini, A. M.; Wang, H. M.; Kwok, W. K.; Whangbo, M. H.; Shirber, J. E. *Science* **1991**, *252*, 1501-1508. (b) Whangbo, M. H.; Torardi, C. C. *Acc. Chem. Res.* **1991**, *24*, 127-133. (c) Ishiguro, T.; Yamaji, K.; Saito, G. “Organic Superconductors”, Springer Verlag, Berlin, 1998. (d) Mori, H. *J. Phys. Soc. Jpn.* **2006**, *75*, 051003/1-15.
3. Lunkenheimer, P.; Hartmann, B.; Lang, M.; Mueller, J.; Schweitzer, D.; Krohns, S.; Loidl, A. *Phys. Rev. B* **2015**, *91*, 245132/1-245132/7.


4. Itahara, H.; Maesato, M.; Asahi, R., Yamochi, H., Saito, G; *J. Electron. Mater.*, **2009**, *38*, 1171-1175.
5. Konarev, D. V.; Kovalevsky, A. Yu.; Coppens P.; Lyubovskaya, R. N.; *Chem. Commun.*, **2000**, 2357-2358.
6. Laukhina, V.; Laukhina, E.; Lebedev, V.; Rovira, C.; Veciana, J. *Proced. Eng.* **2014**, *87*, 1135 – 1138.
7. Chtioui-Gay, I.; Faulmann, C.; de Caro, D.; Jacob, K.; Valade, L.; de Caro, P.; Fraxedas, J.; Ballesteros, B.; Steven, E.; Choi, E. S.; Lee, M.; Benjamin, S. M.; Yvenou, E.; Simonatof, J.-M.; Carellaf, A. *J. Mater. Chem.* **2016**, Advance Article, July 2016.
8. (a) Kurmoo, M.; Graham, A. W.; Day, P.; Coles, S. J.; Hursthouse, M. B.; Caulfield, J. L.; Singleton, J.; Pratt, F. L.; Hayes, W.; Ducasse, L.; Guionneau, P. *J. Amer. Chem. Soc.* **1995**, *117*, 12209-12217. (b) Prokhorova, T. G.; Zorina, L. V.; Simonov, S. V.; Zverev, V. N.; Canadell, E.; Shibaeva, R. P.; Yagubskii, E. B. *CrystEngComm.* **2013**, *15*, 7048-7055. (c) Coronado, E.; Curreli, S.; Giménez-Saiz, C.; Gómez-García, C. J. *Inorg. Chem.*, 2012, *51*, 1111-1126.
9. (a) Coronado, E.; Galán-Mascaros, J. R.; Gomez-Garcia, C. J.; Laukhin, V. *Nature* **2000**, *408*, 447-449. (b) Coronado, E.; Day, P. *Chem. Rev.*, **2004**, *104*, 5419-5448. (c) Coronado, E.; Galán-Mascaros J.R. *J. Mater. Chem.* **2005**, *15*, 66-74.
10. (a) J.R. Lopez, L. Martin, J.D. Wallis, H. Akutsu, Y. Nakazawa, J.-I. Yamada, T. Kadoya, S.J. Coles, C. Wilson, *Dalton Trans*, **2016**, *45*, 9285-9293. (b) Martin, L.; Akutsu, H.; Horton, P.N.; Hursthouse, M.B.; Harrington, R.W.; Clegg, W. *Eur. J. Inorg. Chem.* **2015**, 1865-1870. (c) Coronado, E.; Galan-Mascaros, J.R.; Gomez-Garcia, C.J.; Murcia-Martinez, A.; Canadell, E. *Inorg. Chem.* **2004**, *43*, 8072-8077.
11. (a) Mori, T. *Bull. Chem. Soc. Jpn.* **1998**, *71*, 2509-2526. (b) Mori, T.; Mori, H.; Tanaka, S. *Bull. Chem. Soc. Jpn.* **1999**, *72*, 179-197. (c) Mori, T. *Bull. Chem. Soc. Jpn.* **1999**, *72*, 2011-2027.
12. (a) Krivickas, S.J., Hashimoto, C.; Yoshida, J.; Ueda, A.; Takahashi, K.; Wallis J. D.; Mori, H. *Beil. J. Org. Chem.*, **2015**, *11*, 1561-1569. (b) S. Yang, F. Pop, C. Melan, A.C. Brooks, L. Martin, P. Horton, P. Auban-Senzier, G. L.J.A. Rikken, N. Avarvari, J. D. Wallis, *CrystEngComm.*, **2014**, *16*, 3906-3916.
13. Guionneau, P.; Chasseau, D.; Howard, J.A.K.; Day, P. *Acta Crystallogr.* **2000**, *C56*, 453-454; Pop, F.; Laroussi, S.; Cauchy, T.; Gomez-Garcia, C. J.;

Wallis, J. D. ; Avarvari, N. *Chirality*, **2013**, *25*, 466-474.

14. (a) Data from the Cambridge Structural Database: Allen, F. H. *Acta Crystallogr.* **2002**, *B58*, 380-388. (b) refcode FETMIC, (BEDT-TTF)₂B₅O₆(OH)₄, Brooks, A.C.; Martin, L.; Day, P.; Lopes, E.B.; Almeida, M.; Kikuchi, K.; Fujita, W.; Sasamori, K.; Aktusu H.; Wallis, J.D. *Dalton Trans.* **2013**, *42*, 6645-6654. (c) refcode GAMFIJ20, (BEDT-TTF)₂.Cu(NCS)₂ Hiramatsu, T.; Yoshida, Y.; Saito, G.; Otsuka, A.; Yamochi, H.; Maesato, M.; Shimizu, Y.; Itoe, H.; Kishida, H. *J. Mater. Chem. C* **2015**, *3*, 1378-1388.
15. (a) Avarvari, N.; Wallis, J. D. *J. Mater. Chem.* **2009**, *19*, 4061-4076. (b) Griffiths, J.-P.; Wallis, J. D. *J. Mater. Chem.* **2005**, *15*, 347-365. (c) Brown, R. J.; Brooks, A. C.; Griffiths, J.-P.; Vital, B.; Day, P.; Wallis, J. D. *Org. Biomolec. Chem.* **2007**, *5*, 3172-3182. (d) Yang, S.; Brooks A. C.; Martin, L.; Day, P.; Pilkington, M.; Clegg, W.; Harrington, R. W.; Russo, L.; Wallis, J. D. *Tetrahedron*, **2010**, *66*, 6977-6989.
16. Griffiths, J.P.; Brown, R. J.; Day, P.; Matthews, C. J.; Vital, B.; Wallis, J. D. *Tetrahedron Lett.* **2003**, *44*, 3127-3131.
17. Wang, Q.; Nie, H.; Griffiths, J.-P.; Day, P.; Wallis J. D. *New J. Chem.* **2006**, 1790-1800.
18. (a) Iwahori, F.; Golhen, S.; Ouahab, L.; Carlier, R.; Sutter, J.-P. *Inorg. Chem.* **2001**, *40*, 6541-6542. (b) Setifi, F.; Ouahab, L.; Golhen, S.; Yoshida, Y.; Saito G. *Inorg. Chem.* **2003**, *42*, 1791-1793. (c) Goldenberg, L. M.; Becker, J. Y.; Levi, O. P.-T.; Khodorkovsky, V. Y.; Bryce, M. R.; Petty, M. C. *J. Chem. Soc., Chem. Commun.* **1995**, 475-476. (d) Brooks, A. C.; Day, P.; Dias, S. I. G.; Rabaca, S.; Santos, I. C.; Henriques, R. T.; Wallis, J. D.; Almeida, M. *Eur. J. Inorg. Chem.* **2009**, 3084-3093. (e) Pop, F.; Ding, J.; Daku, L. M. L.; Hauser, A.; Avarvari, N. *RSC Advances*, **2013**, *3*, 3218-3221. (f) Li, G.N.; Wen, D.; Jin, T.; Liao, Y.; Zuo, J.-L.; You, X.-Z. *Tetrahedron Lett.*, **2011**, *52*, 675-678. (g) Hu, L.; Liu, W.; Li, C.-H.; Zhou, X.-H.; Zuo, J.-L. *Eur. J. Inorg. Chem.*, **2013**, 6037-6048.
19. (a) Fourmigué, M.; Batail, P. *J. Chem. Soc. Chem. Commun.* **1991**, 1370-1372. (b) Fourmigué, M.; Uzelmeier, C. E.; Boubekour, K.; Bartley, S. L.; Dunbar, K. R. *J. Organomet. Chem.* **1997**, *529*, 343-350. (d) Avarvari, N. ; Fourmigué, M. *Chem. Commun.* **2004**, 1300-1301.
20. Réthoré, C.; Suisse, I.; Agbossou-Niedercorn, F.; Guillamón, E.; Llusar, R.; Fourmigué, M.; Avarvari, N. *Tetrahedron* **2006**, *62*, 11942-11947.
21. (a) Devic, T.; Avarvari, N.; Batail, P. *Chem. Eur. J.* **2004**, *10*, 3697-3707; (b) Devic, T.; Rondeau, D.; Şahin, Y.; Levillain, E.; Clérac, R.; Batail, P.; Avarvari N. *Dalton Trans.* **2006**, 1331-1337.

22. Chahma, M.; Wang, X. S.; van der Est, A.; Pilkington, M. *J. Org. Chem.* **2006**, *71*, 2750-2755.
23. Lorcy, D.; Bellec, N.; Fourmigué, M.; Avarvari, N. *Coord. Chem. Rev.* **2009**, *253*, 1398-1438.
24. Spek, A. L. *Acta Crystallogr., Sect. D* **2009**, *65*, 148-155.
25. (a) Nyburg, S. C.; Faerman, C. H. *Acta Crystallogr., Sect. B.* **1985**, *41*, 274-279. (b) Hudson, R. F.; Wallis, J. D. *Heterocycles*, **1994**, 1933-1950.
26. Cannizzo, A.; Milne, C. J.; Consani, C.; Gawelda, W.; Bressler, C.; van Mourik, F.; Chergui, M. *Coord. Chem. Rev.*, **2010**, *254*, 2677-2686.
27. (a) Hadadzadeh, H.; Mansouri, G.; Rezvani, A.; Khavai, H. R.; Skelton, B.W.; Makha, M.; Charati, F. R. *Polyhedron*, **2011**, *30*, 2535-2543. (b) Zerara, M.; Hauser, A. *ChemPhysChem*, **2004**, *5*, 395-399.
28. (a) Ballester, P. *Chem. Soc. Rev.* **2010**, *39*, 3810-3830. (b) Conn, M. M.; Rebek, J. Jr. *Chem. Rev.*, **1997**, *97*, 1647-1668.
29. (a) Mendoza, S.; Godinez, L. A.; Kaifer, A. E. *Supramol. Chem.* **2004**, *16*, 165-169. (b) Frei, M.; Diederich, F.; Tremont, R.; Rodriguez, T.; Echegoyen, L. *Helv. Chim. Acta* **2006**, *89*, 2040-2057. (c) Lyskawa, J.; Sallé, M.; Balandier, J. Y.; Le Derf, F.; Levillain, E.; Allain, M.; Viel P.; Palacin, S. *Chem. Commun.* **2006**, 2233-2235. (d) Zhao, B. T.; Blesa, M. J.; Mercier, N.; Le Derf, F.; Sallé, M. *Supramol. Chem.* **2005**, *17*, 465-468.
30. Canevet, D.; Sallé, M.; Zhang, G.; Zhang, D.; Zhu, D. *Chem. Commun.* **2009**, 2245-2269.
31. (a) Ota, A.; Ouahab, L.; Golhen, S.; Cador, O.; Yoshida, Y.; Saito, G. *New. J. Chem.* **2005**, *29*, 1135-1140. (b) Rabu, P.; Drillon, M.; Iwamura, H.; Görlitz, G.; Itoh, T.; Matsuda, K.; Koga, N.; Inoue, K. *Eur. J. Inorg. Chem.* **2000**, 211-216. (c) Okada, K.; Nagao, O.; Mori, H.; Kozki, M.; Shiomi, D.; Sato, K.; Takui, T.; Kitagawa, Y.; Yamaguchi, K. *Inorg. Chem.* **2003**, *42*, 3221-3228. (d) Kumada, H.; Sakane, A.; Koga, N.; Iwamura, H. *Dalton Trans.* **2000**, 911-914. (e) Hicks R. G.; Lemaire, M. T.; Thompson, L. K.; Barclay, T. M. *J. Amer. Chem. Soc.* **2000**, *122*, 8077-8078. (f) Barclay, T. M.; Hicks, R. G.; Lemaire, M. T.; Thompson, L. K. *Inorg. Chem.* **2001**, *40*, 5581-5584.
32. McCann, S.; McCann, M.; Casey, R. M. T.; Jackman, M.; Devereux, M.; McKee, V. *Inorg. Chim. Acta* **1998**, *279*, 24-29.

33. (a) Wysocki, W.; Branowska, D.; Urbanczyk-Lipkowska, Z.; Karczmarzyk, Z. X-ray Structure Analysis Online, **2006**, 22, x51-x52. (b) Constable, E. C.; Housecroft, C. E.; Neuburger, M.; Price, J. R.; Zampese, J. A. *CrystEngComm* **2010**, 12, 2928-2937. (c) Constable, E. C.; Housecroft, C. E.; Neuburger, M.; Price, J. R.; Zampese, J. A. *Aust. J. Chem.* **2010**, 63, 1334-1341.
34. Griffiths, J.-P.; Arola, A. A.; Appleby, G.; Wallis, J. D. *Tetrahedron Lett.*, **2004**, 45, 2813-2816.
35. (a) Kilner, C.A.; Halcrow, M.A. *Dalton Trans*, **2010**, 39, 9008-9012. (b) Enachescu, C.; Krivokapic, I.; Zerara, M.; Real, J.A.; Amstutz, N.; Hauser, A. *Inorg. Chim. Acta* **2007**, 360, 3945-3950.
36. Sheldrick, G. M. *Acta Crystallogr. Sect. A* **2008**, 64, 112-122.
37. Macrae, C. F.; Edgington, P. R.; McCabe, P.; Pidcock, E.; Shields, G. P.; Taylor, R.; Towler, M.; van de Streek, J. *J. Appl. Crystallogr.* **2006**, 39, 453-457.
38. Farrugia, L. J. *J. Appl. Crystallogr.* **1997**, 30, 565-565.
39. Persistence of Vision Pty. Ltd. (2004). Persistence of Vision (TM) RaytracePersistence of Vision Pty. Ltd., Williamstown, Victoria, Australia, <http://www.povray.com/> accessed 6 November 2011
40. Fletcher, D. A.; McMeeking, R. F.; Parkin, D. "The United Kingdom Chemical Database Service", *J. Chem. Inf. Comput. Sci.* **1996**, 36, 746-749.

For Table of Contents Only

BEDT-TTF functionalized with a 2,2'-bipyridin-4-thiomethyl side chain reacts with Fe(II) to form a capsule structure, characterized by X-ray crystallography, which is composed of two *tris*(ligand)Fe(II) complexes which are organized so that the ends of the sulfur donors from one complex lie in the clefts between bipy units on the second donor and *vice-versa*. Further coordination chemistry of this ligand and of the corresponding 4'-terpy ligand with transition metal ions is reported.